

Technical Data Sheet

AL 822

NOMINAL COMPOSITION

Aluminum	$22.0\% \pm 1.0\%$
Zinc	Remainder
Other Elements (Each)	0.05% Max
Other Elements (Total)	0.15% Max

PHYSICAL PROPERTIES

Color	Grayish-White
Melting Point (Solidus)	800°F (441°C)
Flow Point (Liquidus)	900°F (482°C)
Brazing Range	900°F - 1000°F (482°C - 537°C)
Specific Gravity	5.25
Density (Lbs/in ³)	0.190
Electrical Conductivity (%IACS) ⁽¹⁾	N/A
Electrical Resistivity (Microhm-cm)	N/A
⁽¹⁾ IACS = International Annealed Copper Standard	

PRODUCT USES

AL 822 is a general purpose aluminum brazing filler metal for joining of all brazeable grades of aluminum and aluminum alloys when using open air heating methods.

PROPERTIES OF BRAZED JOINTS

The properties of a brazed joint are dependent upon numerous factors including base metal properties, joint design, metallurgical interaction between the base metal and the filler metal. Joint clearances of 0.003 - 0.005 in. (.076-.127 mm) per side are optimum for achieving highest joint strength. Joints with increased clearances can still produce adequate joint strengths depending on final operating conditions. Zinc based alloys offer the highest strength in comparison to other commercially available low temperature brazing alloys often surpassing shear strengths of 18,000 PSI as long as proper joint design techniques are implemented.

AVAILABLE FORMS

Wire, engineered preforms, specialty preforms per customer specification.

SPECIFICATIONS

AL 822 alloy conforms to the following specifications: N/A

APPLICABLE PRODUCT CODE(S)

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: 62-822.

SAFETY INFORMATION

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for AL 822.



Technical Data Sheet

WARRANTY CLAUSE

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.