MASON INDUSTRIES, Inc.

Manufacturers of Vibration Control Products

350 Rabro Drive
Hauppauge, NY 11788
631/348-0282
FAX 631/348-0279
Info@Mason-Ind.com

2101 W. Crescent Ave., Suite D
Anaheim, CA 92801
714/535-2727
FAX 714/535-5738
Info@MasonAnaheim.com

www.Mason-Ind.com

JOB NAME _____

CUSTOMER _____

CUSTOMER P.O. _____

MASON M. _____

DWG No. _____

WHR

Minimal 0.2" 5mm Deflection LDS Hanger for Wire Attachment Freq 12 Hz



LDS stands for **L**ow **D**ynamic **S**tiffness AASHTO Bridge Bearing Natural Rubber to minimize noise and vibration transmission. Maximum Dynamic Stiffness is 1.4.

TYPE WHR RATINGS

Size	Durometer	Rated Capacity Range (lbs)	Rated Capacity Range (kg)	Max. Rated Deflection (in)	Max. Rated Deflection (mm)
40-Green	40	Up to 60	Up to 27	0.20	5
50-Red	50	55 - 95	25 - 43	0.20	5
60-White	60	90 - 155	41 - 70	0.20	5
70-Yellow	70	150 - 220	68 - 100	0.20	5

NOTE: Standard sizes shown.
For heavier capacities, consult factory.

AASHTO Bridge Bearing Natural Rubber Specifications

ORIGINAL PHYSICAL PROPERTIES			TESTED FOR AGING				COMPRESSION SET	LONG TERM CREEP
			OVEN AGING(70hrs/158°F)			OZONE		
Tests: ASTM D-2240 & D-412			ASTM D-573			ASTM D-1149	ASTM D-395	ISO8013
Durometer Shore A	Tensile Strength (min)	Elongat. at Break (min)	Hardness (max)	Tensile Strength (max)	Elongat. at Break (max)	25 pphm in air by Vol. 20% Strain 100°F	22hrs/158°F Method B	168hrs
40±5	2000 psi	500%	+10%	-25%	-25%	No Cracks	25%(max)	5%(max)
50±5	2250 psi	450%	+10%	-25%	-25%	No Cracks	25%(max)	5%(max)
60±5	2250 psi	400%	+10%	-25%	-25%	No Cracks	25%(max)	5%(max)
70±5	2250 psi	300%	+10%	-25%	-25%	No Cracks	25%(max)	5%(max)

NOTE: AASHTO does not spec 40 Duro. 40 Duro by Mason.

MASON LAYOUT DRAWING NO. _____

SIZE	QTY.	TAG

Certification Form S-671 06/2009	DWN	CHKD	DATE	DWG No.