


Premium Extreme Weather Foil Tape



Backing:	1.75 mil Aluminum Foil
Adhesive:	Acrylic
Liner:	Polycoated Natural Kraft Paper
Colors:	Aluminum
Specifications:	UL 723 Classified ($\leq 72\text{mm}$) Meets FAR 25.853(a)
Standard Sizes:	48mm x 46M, 72mm x 46M

Applications

- Taping joints and seams in duct work for A/C, heating, and ventilation systems
- Insulation seaming and patching
- Sealing insulation and repairing in cooler/refrigeration applications
- General purpose industrial and automotive uses
- Aircraft sealing and masking
- Window mask to protect aircraft canopies, windshields and passenger window surfaces from crazing or hazing during paint stripping

Features

Benefits

- | | |
|---|--|
| <ul style="list-style-type: none"> 1.75 mil Aluminum Foil Backing High Performance Acrylic Adhesive | <ul style="list-style-type: none"> Conformable to fit corners and joints UV, moisture, and mold resistant Low odor High tack, aggressive bond to surfaces Excellent performance in extreme cold or heat |
| <ul style="list-style-type: none"> Code Approved Low VOC Content | <ul style="list-style-type: none"> Meets flammability requirements for use in construction, aerospace and marine applications Can contribute toward satisfying EQ Credit 4.1 (Low Emitting Materials) under LEED® |

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness	3.5 mils	0.089 mm	ASTM D-1000
Foil Thickness	1.75 mils	0.044 mm	ASTM D-1000
Adhesion to Steel	55 oz/in	6.02 N/cm	PSTC-101
Tensile Strength	14 lb/in	24.52 N/cm	ASTM D-1000
Operating Temperature	-35 to 260 °F	-37 to 127 °C	
Minimum Application Temp	-5 °F	-20 °C	
Smoke Developed	0		
Flame Spread	0		
VOC Content	<30 g/L		

Recommended Storage Conditions: 60-80 °F at 40-60% RH
Standard Shelf Life (at 25 °C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.